



Report no. C070363
Pages 2

Determination of the slip resistance of ceramic tiles

Sample 1: REF: 3014.069 (TOPCER INDUSTRIA CERAMICA, LDA)

ITACA, S.A.

Castellón, 26 February 2007



1 Background

On 15 February 2007 the Instituto de Tecnología Cerámica (ITC) received a sample of ceramic tiles supplied by ITACA, S.A., identified by the following reference:

- Sample 1: REF: 3014.069 (TOPCER INDUSTRIA CERAMICA, LDA)

The sample consisted of 7 ceramic tiles with the following characteristics: dry-pressed, unglazed, and measuring 300 mm x 300 mm.

The determination of their USRV slip resistance value by the pendulum method was requested.

This report is a full translation of our report C070362 issued on 26 February 2007.

2 Tests conducted

The test has been conducted in accordance with the method set out in standard UNE-ENV 12633:2003 "Method of determination of unpolished and polished slip/skid resistance value". The procedure described in Annex A of this standard has been followed to determine the unpolished slip resistance value (USRV).

The instrument consists of a pendulum arm, 510 mm long, with a rubber slider of hardness IRHD 59±4, measuring approximately 76 x 25 mm, mounted on the end of the arm. The height of the instrument is adjusted so that the slider, which bears a constant load of 22.2±0.5N, maintains contact with the surface for a distance of 126±1mm.

The sample is immersed in water for at least 30 minutes before the test. Each tile is tested in two opposite directions (0° and 180°) with the tile surface saturated with distilled water.

3 Results


Sample 1: REF: 3014.069 (TOPCER INDUSTRIA CERAMICA, LDA)

Table 1

Tile	Direction	USRV value	Average USRV value
1	0°	24	25
	180°	25	
2	0°	25	25
	180°	25	
3	0°	25	25
	180°	25	
4	0°	25	25
	180°	25	
Average value			25

Report no. C070363, issued at the request of ITACA, S.A., consists of a title page and 2 pages.

Castellón, 26 February 2007



Adoración Muñoz Lázaro

Head of the Finished Product
Laboratory

LIABILITY CLAUSES

- The results, conclusions and/or recommendations contained in this report are based on the tests conducted and/or information supplied by the requester.
- No liability is accepted for sampling accuracy and representativeness, unless sampling has been performed by ITC. Unless expressly stated, the samples and their references have been freely chosen by the requester.
- All rights reserved. The content of this report enjoys the protection afforded by law and may not be reproduced, distributed, transformed, or publicly communicated, either wholly or in part, without the express authorisation of the Instituto de Tecnología Cerámica - AICE.
- ITC cannot be held liable for any use that the requester or any other person or body may make of the data or indications contained in this report, whether in benefit of or in detriment to any trade names which the requester may have cited in identifying the studied samples.
- This report has an exclusively commercial character and may not be used in any legal or administrative proceedings as an expert opinion without the express authorisation of ITC.
- The reports issued by ITC may include any analyses, remarks or whatever other assessment might be deemed necessary, even though such indications may not have been expressly requested.
- ITC guarantees the confidentiality of the content of the present report.